

TEST REPORT



Your Ref:

Date: 2003-10-17

Our Ref: 57S034105-1-LHY

Page: 1 of 2

DID: 68851329 / 68851322

Fax: 67784301

NOTE: This Report is issued subject to the "Terms and Conditions Governing Technical Services" set out in the "Request for Technical Services" form. The terms and conditions governing the issue of this report are set out overleaf.

Subject : Testing of one sample of thermoplastic road marking material

Client : Dau Long Road-Mark Materials Co., Ltd
No. 6 Zihciang 3rd Rd.,
Nankang Industrial Park,
Nantou City, 540
Taiwan

Attn : Ms May Tzeng

Sample Submission

Date : 2003-08-22

Sample

Description : One sample of 'Dau Long' thermoplastic road marking material marked as follows, was submitted for testing :

Sample Marked : Dau Long Thermoplastic Striping Material White

Type : DH-92W

Quantity : 25 kg

Method of Test :

BS 3262 : Part 1 : 1989
"Hot-applied Thermoplastic Road Marking Materials"

Two handwritten signatures in black ink, one above the other, located in the bottom right corner of the page.



Your product quality and safety mark

Results :Table A

Test Item	DH-92W White	BS 3262 : Part 1 : 1989 Specification
1. Softening point, °C	95	65 min
2. Luminance factor, %	77	70 min
3. Heat stability on luminance factor, %	77	65 min
4. Flow resistance at 40 ±2°C, %	5.0	25 max


Table B

Test Item	DH-92W White	BS 3262 : Part 1 : 1989 Specification
1. Binder content, % m/m of mixture	21.1	18 - 22
2. Corrected Glass Beads content, % m/m of mixture	36.7	20 min
3. Percentage Passing 2.80 mm Sieve	100	100
4. Percentage Passing 600 µm Sieve	71	65 - 95
5. Aggregate, Pigment, Extender and Solid Glass Beads, % m/m of mixture	78.9	78 - 82
6. Skid resistance, units	50	45 min

Remarks : Test items in **Table B** were conducted by Celtest Limited, United Kingdom.



LAI HOCK YAM, PHILIP
TECHNICAL EXECUTIVE



WONG-LINTAI HOE (MRS)
PRODUCT MANAGER
TESTING GROUP (COATINGS)